

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 9148 (1979): Tape wrapped rectangular and square copper wires with a temperature index of 220 [ETD 33: Winding Wire]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



IS : 9148 - 1979

Indian Standard

SPECIFICATION FOR
TAPE WRAPPED RECTANGULAR
AND SQUARE COPPER WIRES WITH
A TEMPERATURE INDEX OF 220

UDC 621.315.336.96-418 621.3.045



© Copyright 1979

INDIAN STANDARDS INSTITUTION
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

August 1979



AMENDMENT NO. 1 MARCH 1985

TO

IS:9148-1979 SPECIFICATION FOR TAPE WRAPPED
RECTANGULAR AND SQUARE COPPER WIRES WITH
A TEMPERATURE INDEX 220

(Page 3, clause 1.1) - Substitute the following
for the existing clause:

'1.1 This standard relates to polyimide tape, wrapped
rectangular and square copper conductors suitable
for temperature index 220'.

(Page 3, clause 1.2, first line) - Insert
'polyimide' in between 'the' and 'tape'.

(ETDC 33)

Reprography Unit, ISI, New Delhi, India

Indian Standard

SPECIFICATION FOR TAPE WRAPPED RECTANGULAR AND SQUARE COPPER WIRES WITH A TEMPERATURE INDEX OF 220

Winding Wires Sectional Committee, ETDC 33

Chairman

SHRI K. DORAISWAMY
Five Star Apartments, Bund Garden Road, Pune

Members

SHRI S. B. BAPAT
SHRI N. S. SRETH (*Alternate*)
SHRI J. L. CHHABRA

SHRI J. S. PASSI (*Alternate*)
SHRI K. DAS GUPTA
SHRI GOPAL NARAIN (*Alternate*)
SHRI S. G. DESHMUKH
SHRI F. J. MEHTA (*Alternate*)

SHRI P. GHOSH
SHRI T. CHOWDHURY (*Alternate*)

SHRI S. C. GOELA
SHRI B. RAMAN (*Alternate*)
SHRI S. AMEERJAN (*Alternate*)

SHRI P. K. GOPALAN
SHRI V. M. JOSHI (*Alternate*)

SHRI D. P. GUPTA

SHRI K. GURURAJA

SHRI R. SOMASEKHARA (*Alternate*)

SHRI P. N. HIRIYANNAIAH

LT-COL A. P. JAIN

SHRI SAT DEV (*Alternate*)

Representing

Dr Beck & Co (India) Ltd, Pune

Directorate General of Supplies and Disposals
(Inspection Wing), New Delhi

Indo-American Electricals Ltd, Calcutta

Bharat Bylee Ltd, Bombay

Indian Cable Co Ltd, Calcutta

Bharat Heavy Electricals Ltd, Bhopal

Wandleside National Conductors Ltd, Pune

Directorate General of Technical Development,
New Delhi

Bharat Electronics Ltd, Bangalore

Kirloskar Electric Co Ltd, Bangalore

Raksha Mantralaya, Manakikaran Nidishalaya,
New Delhi

(Continued on page 2)

© Copyright 1979

INDIAN STANDARDS INSTITUTION

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

IS : 9148 - 1979

(Continued from page 1)

<i>Members</i>	<i>Representing</i>
SHRI D. K. KULKARNI	Jyoti Ltd, Vadodara
SHRI B. G. SHARMA (Alternate)	
SHRI D. R. MANOHAR	The National Insulated Cable Co of India Ltd, Calcutta
SHRI J. S. BHAN (Alternate)	
SHRI D. D. MEHTA	Shakti Insulated Wires Pvt Ltd, Bombay
SHRI S. NAGARAJAN (Alternate)	
SHRI S. K. MUKHERJI	National Test House, Calcutta
SHRI A. NANDKEOLYAR	Railway Board (Ministry of Railways)
SHRI D. K. BANSAL (Alternate)	
SHRI P. F. PARIKH	Winding Wires Manufacturers' Association of India, Bombay
PROF N. SEN (Alternate)	
DR G. M. PHADKE	Indian Electrical Manufacturers' Association, Calcutta
SHRI D. B. GUPTA (Alternate)	
SHRI A. K. RAMAN	Asian Cables Corporation Ltd, Bombay
SHRI P. V. RAO	Indian Telephone Industries Ltd, Bangalore
SHRI J. NAGESH BHATT (Alternate)	
SHRI N. P. SANGAMPSWARAN	Devidayal Electronics and Wires Ltd, Bombay
SHRI P. S. LAMBA (Alternate)	
SHRI Y. K. SHAH	Philips India Ltd, Bombay
SHRI A. M. GHATAK (Alternate)	
SHRI A. N. SRIVATHSA	NGEF Ltd, Bangalore
SHRI V. KRISHNAMURTHY (Alternate)	
SHRI S. P. SACHDEV, Director (Elec tech)	Director General, ISI (Ex-officio Member)

Secretary

SHRI DIPAK DASDE
Assistant Director (Elec tech), ISI

Indian Standard

SPECIFICATION FOR
TAPE WRAPPED RECTANGULAR
AND SQUARE COPPER WIRES WITH
A TEMPERATURE INDEX OF 220

0. FOREWORD

0.1 This Indian Standard was adopted by the Indian Standards Institution on 29 March 1979, after the draft finalized by the Winding Wires Sectional Committee had been approved by the Electrotechnical Division Council.

0.2 While preparing this standard, assistance has been derived from Doc : 55 (Secretariat) 142 'Second Draft — Specification for particular types of winding wires — Tape wrapped rectangular copper wires with a temperature index of 220' issued by International Electrotechnical Commission.

0.3 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test, shall be rounded off in accordance with IS : 2-1960*. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

1. SCOPE

1.1 General — This standard relates to tape wrapped rectangular and square copper conductors suitable for temperature index of 220.

1.2 The tape shall be coated with a suitable adhesive (for example, fluorinated ethylene propylene). After wrapping the covering shall be heat-sealed to form a continuous and adherent sheath.

1.3 Sizes — The requirements of this standard are applicable to conductors having thicknesses from 0.80 up to and including 5.6 mm and widths from 2 up to and including 16 mm. A schedule of preferred sizes is given in IS : 6160-1971†.

*Rules for rounding off numerical values (*revised*).

†Specification for rectangular conductors for electrical machines.

IS : 9148 - 1979

1.4 Grades of Covering — Three grades of covering are specified:

- a) Fine (F),
- b) Medium (M), and
- c) Thick (T).

In each category, single tape and double tape coverings are specified.

2. TERMINOLOGY

2.0 For the purpose of this standard, the following definitions shall apply.

2.1 Wire — The insulated material as received.

2.2 Conductor — The bare metal after removal of the covering.

2.3 Increase in Dimension due to Covering — The difference between the thickness over the tape covering and the thickness of the conductor.

2.4 Tolerance — The permissible divergence of an actual magnitude from that prescribed.

3. GENERAL TEST CONDITIONS

3.1 Unless otherwise specified all tests shall be carried out within a temperature range of 15 to 35°C and a relative humidity range of 45 to 75 percent. Before measurements are made, the specimens shall be preconditioned under these atmospheric conditions for a time sufficient to allow specimens to reach stability.

3.2 The wire to be tested shall be removed from the packaging in such a way that the wire should not be subjected to tension or unnecessary bends.

3.3 Before each test sufficient wire shall be discarded to ensure that any damaged wire is not included in the test specimens.

3.4 When no specific range of sizes is given for a test, the test is applicable to all sizes.

4. CONDUCTOR

4.1 The conductor shall conform to **3.1** of IS : 6160-1971*.

5. APPLICATION OF TAPE COVERING

5.1 General — Before covering, the conductor shall be completely free from surface defects like burrs, copper dust, etc.

*Specification for rectangular conductors for electrical machines.

5.2 Arrangement of Layers

5.2.1 Either one or two layers of tape may be applied.

5.2.2 The tape shall be wrapped on the conductor, tightly, evenly and free from creases or wrinkles, with the adhesive on the inside when one side coated.

5.2.3 The tape shall be applied with an overlap of 45 to 50 percent and when two layers are used they shall be applied in the same direction and displaced by approximately 25 percent of the tape width.

5.2.4 After wrapping, the tape shall be heat-sealed by suitable means to form an adherent and continuous sheath.

5.3 **Increase in Dimensions due to Covering** — The increase in dimensions due to covering when determined by the method as described in 5.1 of IS : 3855 (Part II)-1979* shall lie between the minimum and maximum values given in Table 1.

TABLE 1 INCREASE IN DIMENSIONS DUE TO COVERING

GRADE OF COVERING	INCREASE IN DIMENSIONS DUE TO SINGLE TAPE COVERING		INCREASE IN DIMENSIONS DUE TO DOUBLE TAPE COVERING	
	Min	Max	Min	Max
(1)	(2)	(3)	(4)	(5)
	mm	mm	mm	mm
Fine (F)	0.080	0.160	0.160	0.320
Medium (M)	0.150	0.250	0.300	0.500
Thick (T)	0.240	0.360	0.480	0.720

NOTE — The overall dimensions shall not exceed the maximum dimensions permitted for the conductor plus maximum values.

5.4 Flexibility and Adherence

5.4.1 *Flexibility (Mandrel Winding Test)* — The covering shall show no opening or delamination when bent on the edge and on the flat around a mandrel having a diameter 4 times the width and thickness respectively.

5.4.2 *Adherence* — A specimen of the wire, 200 to 250 mm long, shall be clamped between the grips of testing machine. The covering shall

*Specification for rectangular and square enamelled copper conductors: Part II Methods of tests (first revision).

IS : 9148 - 1979

be cut through circumferentially at a point approximately half way along the measured length. The wire shall be stretched 15 percent for single covering and 10 percent for double covering at a rate of 1 to 5 mm/s.

The distance of loss of adhesion shall be less than the conductor width.

5.5 Heat Shock — The covering shall show no opening or delamination when prepared as described in 5.4.1 and subjected to a temperature of 240 to 245°C for 30 minutes.

NOTE — The requirements of delamination test are under consideration

5.6 Breakdown Voltage — The breakdown voltage test shall be carried out in accordance with Appendix A on five samples. At least four out of the five samples tested shall not breakdown at voltages less than those given in Table 2 and the fifth sample shall not breakdown at the voltage less than 50 percent of the value specified.

TABLE 2 BREAKDOWN VOLTAGE

GRADE OF COVERING	NOMINAL CONDUCTOR THICKNESS		BREAKDOWN VOLTAGE, <i>Min</i>	
	Over	Up to and Including	Single Tape	Double Tape
(1)	(2)	(3)	(4)	(5)
	mm	mm	V (rms)	V (rms)
Fine (F)	—	2 500	2 000	3 000
Medium (M)			3 000	5 000
Thick (T)			4 000	7 000
Fine (F)	2·500	5 600	1 500	2 500
Medium (M)			2 300	3 500
Thick (T)			3 000	5 000

APPENDIX A

(Clause 5.6)

BREAKDOWN VOLTAGE

A-1. TEST VOLTAGE

A-1.1 The test voltage shall be alternating and of a nominal frequency of 50 Hz and approximately sinusoidal, the peak factor being within the limits of $\sqrt{2} \pm 5$ percent (1.34 to 1.49). The test transformer should have a rating of at least 500 VA and should provide a current of essentially undisturbed waveform under test conditions. The test transformer shall have a trip current setting of not more than 5 mA.

A-1.2 The voltage is applied at zero and increased at a uniform rate of approximately 100 V per second until breakdown occurs. In the event of breakdown occurring in less than 5 seconds the rate of increase of voltage shall be reduced. Where the breakdown voltage is equal to or greater than 2 500 V, the rate of rise of voltage shall be 500 V per second.

A-2. METHOD


A-2.1 A specimen of wire 350 mm long shall have the tape removed at one end and be bent flatwise around a mandrel as shown in Fig. 1.

The radius of the mandrel shall be:

25 mm for wires with thicknesses up to and including 2.5 mm, and
50 mm for wires with thicknesses over 2.5 mm.

The test specimen shall be immersed in a metal container which shall be filled, as shown in Fig. 1, with nickel shot, nickelplated shot or stainless steel ball bearings not more than 2.0 mm in diameter maintained in a clean condition by washing it, for example, in trichloroethylene.

A-2.2 The test voltage shall be applied between the bare conductor and metal shots (which are earthed).



t = nominal thickness of tape wrapped copper conductor.

All dimensions in millimetres.

FIG. 1 ARRANGEMENT FOR BREAKDOWN VOLTAGE TEST
USING SHOT BATH

INTERNATIONAL SYSTEM OF UNITS (SI UNITS)

Base Units

QUANTITY	UNIT	SYMBOL
Length	metre	m
Mass	kilogram	kg
Time	second	s
Electric current	ampere	A
Thermodynamic temperature	kelvin	K
Luminous intensity	candela	cd
Amount of substance	mole	mol

Supplementary Units

QUANTITY	UNIT	SYMBOL
Plane angle	radian	rad
Solid angle	steradian	sr

Derived Units

QUANTITY	UNIT	SYMBOL	DEFINITION
Force	newton	N	1 N = 1 kg m/s ²
Energy	joule	J	1 J = 1 N.m
Power	watt	W	1 W = 1 J/s
Flux	weber	Wb	1 Wb = 1 V.s
Flux density	tesla	T	1 T = 1 Wb/m ²
Frequency	hertz	Hz	1 Hz = 1 c/s (s ⁻¹)
Electric conductance	siemens	S	1 S = 1 A/V
Electromotive force	volt	V	1 V = 1 W/A
Pressure, stress	pascal	Pa	1 Pa = 1 N/m ²

INDIAN STANDARDS INSTITUTION

Manak Bhavan 9 Bahadur Shah Zafar Marg NEW DELHI 110002

Telephones : 26 60 21, 27 01 31

Telegrams : Manaksanstha

Regional Offices

		Telephone
Western	Novelty Chambers Grant Road	BOMBAY 400007 37 97 29
Eastern	5 Chowringhee Approach	CALCUTTA 700072 23-08 02
Southern	C. I. T. Campus Adyar	MADRAS 600020 41 24 42

Branch Offices :

Pushpak	Nurmohamed Shaikh Marg, Khanpur	AHMADABAD 380001 2 03 91
F' Block,	Unity Bldg, Narasimharaja Square	BANGALORE 560002 2 76 49
Gangotri Complex,	Bhadbhada Road, T. T. Nagar	BHOPAL 462003 6 27 16
22E Kalpana Area		BHUBANESHWAR 751014 5 36 27
Ahimsa Bldg,	SCO 82-83, Sector 17C	CHANDIGARH 160017 2 83 20
6-8-56/57 L, N	Gupta Marg	HYDERABAD 500001 22 10 83
D-277 Todarmal Marg,	Banipark	JAIPUR 302006 6 98 32
117/418 B Sarvodaya Nagar		KANPUR 208005 8 12 72
B.C.I. Bldg (3rd Floor),	Gandhi Maidan East	PATNA 800004 6 36 55
Hantex Bldg (2nd Floor)	Rly Station Road	TRIVANDRUM 695001 32 27

Printed at Printograph, New Delhi, India